



LCR Hallcrest Ltd.
Riverside Buildings, Dock Road,
Connah's Quay, Flintshire,
CH5 4DS U.K.
Tel: +44 (0)1244 817107
Fax: +44 (0)1244 818502
Email: sales@hallcrest.uk.com
Web: www.hallcrest.uk.com

Advanced Thermographic Technologies

Technical Product Information

CHAMELEON PHOTOCHROMIC WATER BASED TEXTILE SCREEN PRINTING INK

Functionionality: Reversible Photochromic Ink

Article No:

Revision: 02

Last Revision: 15/01/2013

Description

Water based Photochromic textile screen ink for textile substrates.

The ink is supplied as a 1 part ink system ready formulated and easy to use allowing flexibility in application and optimisation in appearance of printed article.

Application

CHAMELEON water based Textile screen printing ink suited to flat bed screen printing processes. As with all colour changing inks the printed effect is dependent upon several factors including substrate, drying time, temperature and mesh count. The printed article exhibits a matt finish when printed.

Product Properties

Photochromic properties

CHAMELEON water based Photochromic textile screen ink is available in various colours (blue, yellow, purple, red, Orange and other colours upon request and against minimal volume order). Water based Photochromic textile screen ink becomes intensely colored after only 15 seconds of direct sun light exposure and return to clear after approximately 5 minutes out of any source of UV light. The different colours fade to clear at different rates. Orange and yellow are the slowest to return back to clear. Yellow even requires visible light to return back to clear. If an exposed print or coat is put in a dark area, the yellow will not fade until it is left in normal room light (visible light) for a few minutes. The color change is reversible. When measured in the same conditions with varying temperatures, the colour intensity generated by the Water based Photochromic textile screen ink is reduced at high temperatures (50 C) when compared to lower temperatures (less than 25 C).

Standard colours	Blue, yellow,, purple
Special colours	Red, orange, other colour available upon request

Light Fastness

Photochromic inks are inherently susceptible to damage by UV light. Protections by incorporating UV absorbers in a Overprint varnish will reduce accordingly the colour intensity. Addition of HALS in the OPV can be considered but should be evaluated prior to commercial use.

Light fastness properties of supplied colours are as follows:*

Blue Purple Red Orange Yellow 1-2

*Rating according to measurement on Blue Wool Scale

Adhesion

The ink is well suited for natural fibres

Due to the wide variety of substrates it is recommended that this ink is evaluated fully prior to any commercial use.

Rub Resistance

Has high dry and wet fastness properties and hand washing resistance if polymerized accordingly. Printed article is not suitable for Machine Washing.

Additional Product Properties

Pigment Content (%)	24 ± 2%
Pigment Size (µm)	95% less than 8 microns
Solid Content (%) ¹	42 ± 3.0
Solvent	Water
Supplied Viscosity (cps) ²	>5000

¹ AMB50 Moisture Content Analyzer

² Mixed ink measured on a LVT Brookfield Viscometer @ 25°C / 77°F

Recommended Printing Parameters

Screen Configuration

The optimum screen configuration depends on several factors, the most important of which is the desired colour of the finished product.

The theoretical ink volume of the screen is crucial for the desired effect. Using a higher theoretical ink volume will increase the intensity of colour of the product.

Recommended Mesh Size	90T
Minimum Mesh Size	150T

Do not allow the ink to sit dormant on the screen as this will cause drying in/on the screen and affect print definition and quality. Always keep the screen flooded with ink and when air temperature is high, spray water on top of the ink to avoid drying.

Dilution

The printing ink is supplied in a format that once mixed is at printing viscosity. The ink should not be thinned. Water should never be used to dilute this system.

Drying

The ink should be cured at 130°C for 2 to 3 minutes.

Cleaning recommendations

CHAMELEON® Water Based Textile Screen Ink should be cleaned on screen using water only. Glycol based cleaners should not be used as these will damage the function of the ink.

After use screens can be cleaned with water. A high powered water jet may be required to remove all ink remnants.

Handling

CHAMELEON ® Water Based Textile Screen Ink is a 1 part ink system that will remain stable if stored in the correct storage conditions.

Do not mix with other ink systems.

Storage

CHAMELEON ® Water Based Textile Screen Ink should be stored away from solvents, sources of UV light and high temperature to gain optimum performance from the product.

Shelf Life of Mixed Ink

3 Months

Do not store in temperatures in Excess of 25°C / 77°F

Do not freeze. As the product is water based it is important to keep the containers tightly shut to avoid evaporation and skinning of the product.

Please consult Material Safety Data Sheet before use

Information in this Product Data Sheet is compiled from our general experience and data obtained from various technical publications. While we believe that the information provided herein is accurate at the date hereof, no responsibility for its completeness or accuracy can be assumed. Tests are carried out under controlled laboratory conditions. Information is given in good faith, but without commitment as conditions vary in every case. The information is provided solely for consideration, investigation and verification by the user. We do not except any liability for any loss, damage or injury resulting from its use (except as required by law). Please refer to the Material Safety Data Sheet before using products to ensure safe handling.